

CIKOpoxy FC

Smart Chemical Solutions



Epoxy Resin Based Resurfacing Putty

Description

CIKOpoxy FC is a two component epoxy resin based resurfacing compound to repair expansion joints, control joints, cracks, deep holes worn and eroded slabs.

CIKOpoxy FC is suitable to fill and seal cavities and cracks in structural components up to 3 mm wide.

CIKOpoxy FC is based on epoxy cured with a special grade of hardener. It offers excellent bonding properties to wide range of substrates.

Properties

- Two components thixotropic, solvent free epoxy resin, graded filler and thixotropic agents.
- Resurfacing materials for horizontal, vertical and overhead applications
- Re-profiling small area up to 20mm thickness
- Exhibits good wear and abrasion resistance.
- Resistance to impact load.
- Provides high strength and non-sag properties.
- Resistance to wide range of aggressive chemicals.
- Withstands dynamic and static heavy loads.

Application area

CIKOpoxy FC acts as a resurfacing material suitable for:

- Bedding and gap filling applications in concrete repair.
- Floor and wall resurfacing before application of epoxy or polyurethane range of coatings.
- Crack and holes filling
- Resurfacing the damaged concrete surface n horizontal and vertical planes.

Physical properties

Form	Two component system Part-A : Viscous Paste Part-B : Viscous paste
Solid by mass	% 100
Colour	Grey in general
Mixing ratio	Pre-weighed packs
Pot life @ 25 °C @ 35 °C	≥ 90 min Approx 45 min
Final cure	7 days
Over coating time @ 25 °C	After 24 hours
Compressive Strength @ 7 days ASTM C579	>60 MPa
Bond strength	Failure in concrete

Coverage / Yield

1 .5kg of CIKOpoxy FC will cover 1m² at 1mm thickness.
4.0 Liters kit will cover 4 m² at 1 mm thickness.

Note: The coverage depends on the substrate condition and finish. Consult CIKO technical service department for further guidance.

Chemical resistance

CIKOpoxy FC is resistant to a wide range of chemicals. Specific data is available on request. Resistance to spillages includes:

- Dilute mineral acids
- Hydraulic oil
- Bleach
- Sodium chloride
- Fats
- Kerosene
- Petrol
- Lactic acid 5%
- Vegetable oils
- Mineral solvents

Application instructions

Surface preparation

New concrete substrate:

The new concrete substrate should complete the process of curing and should have a dry surface. The surface should be prepared using mechanical scrubbers to remove loose and un-bonded particles.

Old concrete substrate:

All contamination such as oil / chemical spillage or pot holes should be treated. The surface should be prepared using mechanical scrubbers to remove loose and un-bonded particles.

Mixing

The base [Part-A] and hardener [Part-B] components of CIKOpoxy FC should be mixed thoroughly using a slow speed drill-paddle assembly for two to three minutes and ensure a homogenous mix.

Application

Properly mixed materials should be spread over the cleaned surface using a trowel or putty blade maintaining the required thickness and levelling.

Precautions

- CIKOpoxy FC should not be applied at temperatures below 10 °C.
- The substrate should be clean and dry.

Packaging

4.0 liters kit consisting part A and B.

Shelf life

CIKOpoxy FC has a shelf life of 12 months if stored in accordance with CIKO instructions.

Storage

CIKOpoxy FC should be stored under enclosed shaded area at temperatures between 5 – 35°C.

Health & safety

CIKOpoxy FC should not come in contact with eyes or be swallowed. Ensure adequate ventilation and avoid inhalation of vapors. Applicator should wear appropriate clothes, gloves and goggles. Use of barrier cream is recommended to provide additional skin protection. If comes in contact with eyes, flush with plenty of fresh water and seek medical advice.

Refer Material Safety Data Sheet for further details.

Technical Support

For any technical support, do not hesitate to contact CIKO team at any time as CIKO offers on and off site services to end users, specifier and contractors.

More from CIKO Middle East

A wide range of construction chemical products are manufactured by CIKO Middle East which includes:

- Concrete admixtures and additives
- Waterproofing and damp proof coatings
- Surface treatments
- Flooring and toppings
- Grouts and anchors
- Tile adhesives and grout
- Concrete repair materials
- Adhesives and bonding agent
- Protective coating
- Joint Sealants and Moulding compounds
- Ancillaries

TDS/RP18 Rev.:1 Issue:C

Note: The information presented herein based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control



ص. ب رقم : ٢٩٥ ، الدوحة - قطر
ت : (+974) 4411 4787 / 4411 4790 / 4411 4794
فاكس : (+974) 44114792
+٩٧٤ ٤٤١١ ٤٧٩٤ ، ٤٤١١ ٤٧٩٠ ، ٤٤١١ ٤٧٨٧

P.O.Box : 295, Doha, Qatar
T.: (+974) 4411 4787 / 4411 4790 / 4411 4794
F.: (+974) 44114792
E-mail: enquiries@cikome.com